



Valve Regulated Lead-Acid Rechargeable Battery



BP33-12S


Standard Type

The battery is constructed by plates, separators, safety valves and container. Since the electrolyte is held by a glass-mat separator and plates, the battery can be used in any direction and position without leakage.

PERFORMANCE SPECIFICATIONS


Nominal Voltage(V).....	12 volts(6cells in series)
Nominal Capacity(Ah)	
20 hour rate F.V.(1.75V/cell) (1650mA to 10.5volts)	33.0 Ah
10 hour rate F.V.(1.75V/cell) (3140mA to 10.5volts)	31.4 Ah
5 hour rate F.V.(1.75V/cell) (5610mA to 10.5volts)	28.1 Ah
1 hour rate F.V.(1.55V/cell) (19800mA to 9.30volts).....	19.8 Ah
Approximate Weight.....	11250g(24.8lbs.)
Terminal	
Standard.....	Type B7
Internal Resistance (Fully Charged Battery).....	<9mΩ
Maximum Discharge Current For 5 sec.(A).....	495A
Maximum Charge Current(A).....	9.9A
Ambient Temperature	
Charge.....	0°C(32°F)~40°C(104°F)
Discharge.....	-20°C(-4°F)~50°C(122°F)
Storage.....	-20°C(-4°F)~40°C(104°F)
Vibration test:	
Frequency: 16.7Hz	
Amplitude: 4mm	
Vibrate the battery horizontally or vertically for 60 minutes. The battery have no abnormality.	
Case.....	ABS
Dimension(mm/inch)	
Length ±1.5mm.....	195/7.68
Width ±1.5mm.....	129/5.08
Container Height ±1.5mm.....	155/6.10
Total Height ±2mm.....	179/7.05
Application.....	Wheelchairs, Lawn Mowers, Electronic Medical Equipment, UPS, Golf-Carts.

BP33-12S Battery discharge characteristics (25°C/77°F)



Battery Charging Characteristics


(Typical example of charge characteristics for the standby use)



Charging Procedure



Application	Charging method	Charging Voltage at 20°C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C/cell)	Max. charging current (CA)	Charging time 0.1CA, 20°C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power Source	Constant voltage & Constant current charging (with current restriction)	2.25~2.30	-3	0.3	24	20	0~40 (32~104°F)
For cycle service		2.40~2.50	-4	0.3	16	10	

Effect of Temperature on Long Term Float Life



OUTER DIMENSIONS


mm(inch)




TERMINAL TYPE

mm(inch)

● Terminal B7




[M6 BOLT & NUT]



Constant power discharge characteristics at 25°C/77°F

Final Voltage	Discharge time								
	5Min	10Min	15Min	30Min	1Hr	3Hr	5Hr	10Hr	20Hr
10.80V	1193.1	878.3	703.9	418.8	240.18	96.19	66.32	37.06	19.38
10.50V	1381.0	951.6	736.2	434.7	247.38	98.11	67.32	37.62	19.80
10.20V	1467.3	985.8	759.0	444.7	251.83	99.00	67.69	37.81	19.89
9.90V	1533.2	1009.4	776.5	450.9	254.85	99.69	67.92	37.92	19.94
9.60V	1584.0	1029.6	792.0	455.4	257.40	100.29	68.13	37.92	19.94

TERMINAL POSITION



B.B. BATTERY CO., LTD.

Web Site: <http://www.bb-battery.com>

USA:

B&B BATTERY(USA) INC.
6415 RANDOLPH ST.COMMERCE,
CA,90040 U.S.A.
TEL:1-323-278-1900.1-800-278-8599
FAX:1-323-278-1268
E-Mail:sales@bb-battery.com

EUROPE:

B&B BATTERY(EUROPE) B.V.
3 WIJNGAARDVELD, 9300 AALST,BELGIUM
TEL:(00)32-53781567
FAX:(00)32-53781567
E-Mail:hansdevriese@bb-battery.com

CHINA FACTORY:

B.B. BATTERY CO., LTD.
CHENG DONG TRIAL AREA,HUANG GANG,
RAOPING, GUANG DONG,CHINA,515700
TEL:86-768-7601001-2
FAX:86-768-7601469
E-Mail:maggy@bb-battery.com

HONG KONG:

NATIONAL TRADING LTD.
TEL:852-2301-3800
FAX:852-2739-1182
E-Mail:bbhk@hkstar.com

JAPAN:

B&B BATTERY(JAPAN) CO., LTD.
1375-11 NARAHARA-MACHI,HACHIOJI,
TOKYO 193-0803,JAPAN.
TEL:81-426-25-6375
FAX:81-426-25-6375
E-Mail:miyata@bb-battery.com

TAIWAN:

B.B. BATTERY(TAIWAN) CO., LTD.
TEL:886-6-502-5150
FAX:886-6-589-8087
E-Mail:maggy@bb-battery.com

